

least one other raw material gas at said mixing ratio; ~~and~~

forming a second n-conduction type of gallium nitride group compound semiconductor layer having a low electron concentration and a resistivity which is greater than a resistivity of said first n-conduction type of gallium nitride group compound semiconductor layer, without feeding said silicon-containing gas; and

etching said second n-conduction type of gallium nitride group compound semiconductor layer to expose a surface of said first n-conduction type of gallium nitride group compound semiconductor layer, an n-electrode being formed on said exposed surface of said first n-conduction type of gallium nitride group compound semiconductor layer.

3/ 21/ (Previously presented) A method for producing a gallium nitride group compound semiconductor according to claim 19, wherein said gallium nitride group compound semiconductor comprises  $\text{Al}_x\text{Ga}_{1-x}\text{N}$  ( $0 \leq x \leq 1$ ).

4/ 22/ (Previously presented) A method for producing a gallium nitride group compound semiconductor according to claim 20, wherein said gallium nitride group compound semiconductor comprises  $\text{Al}_x\text{Ga}_{1-x}\text{N}$  ( $0 \leq x \leq 1$ ).

5/ 23/ (Previously presented) A method for producing a gallium nitride group compound semiconductor according to claim 19, wherein said gallium nitride group compound semiconductor comprises GaN.

6/ 24/ (Previously presented) A method for producing a gallium nitride group compound semiconductor according to claim 20, wherein said gallium nitride group compound semiconductor comprises GaN.

7/ 25/ (Original) A method for producing a gallium nitride group compound semiconductor according to claim 19, wherein said conductivity (1/resistivity) is not less than  $3.3/\Omega\text{cm}$ .

8/ 26/ (Original) A method for producing a gallium nitride group compound semiconductor according to claim 21, wherein said conductivity (1/resistivity) is not less than  $3.3/\Omega\text{cm}$ .

27. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 23, wherein said conductivity (1/resistivity) is not less than  $3.3/\Omega\text{cm}$ .

28. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 20, wherein said electron concentration is not less than  $6 \times 10^{16}/\text{cm}^3$ .

29. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 22, wherein said electron concentration is not less than  $6 \times 10^{16}/\text{cm}^3$ .

30. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 24, wherein said electron concentration is not less than  $6 \times 10^{16}/\text{cm}^3$ .

31. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 19, wherein said conductivity (1/resistivity) is ranging from  $3.3/\Omega\text{cm}$  to  $1.3 \times 10^2/\Omega\text{cm}$ .

32. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 21, wherein said conductivity (1/resistivity) is ranging from  $3.3/\Omega\text{cm}$  to  $1.3 \times 10^2/\Omega\text{cm}$ .

33. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 23, wherein said conductivity (1/resistivity) is ranging from  $3.3/\Omega\text{cm}$  to  $1.3 \times 10^2/\Omega\text{cm}$ .

34. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 20, wherein said electron concentration is ranging from  $6 \times 10^{16}/\text{cm}^3$  to  $3 \times 10^{18}/\text{cm}^3$ .

35. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 22, wherein said electron concentration is ranging from  $6 \times 10^{16}/\text{cm}^3$  to  $3 \times 10^{18}/\text{cm}^3$ .

$10^{18}/\text{cm}^3$ .

18  
36. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 24, wherein said electron concentration is ranging from  $6 \times 10^{16}/\text{cm}^3$  to  $3 \times 10^{18}/\text{cm}^3$ .

19  
37. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 19, wherein said gallium nitride group compound semiconductor is formed on or above a buffer layer which is formed on a sapphire substrate.

20  
38. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 20, wherein said gallium nitride group compound semiconductor is formed on or above a buffer layer which is formed on a sapphire substrate.

21  
39. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 21, wherein said gallium nitride group compound semiconductor is formed on or above a buffer layer which is formed on a sapphire substrate.

22  
40. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 22, wherein said gallium nitride group compound semiconductor is formed on or above a buffer layer which is formed on a sapphire substrate.

23  
41. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 25, wherein said gallium nitride group compound semiconductor is formed on or above a buffer layer which is formed on a sapphire substrate.

24  
42. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 28, wherein said gallium nitride group compound semiconductor is formed on or above a buffer layer which is formed on a sapphire substrate.

25  
43. (Original) A method for producing a gallium nitride group compound semiconductor

according to claim 31, wherein said gallium nitride group compound semiconductor is formed on or above a buffer layer which is formed on a sapphire substrate.

44. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 34, wherein said gallium nitride group compound semiconductor is formed on or above a buffer layer which is formed on a sapphire substrate.

45. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 37, wherein said buffer layer is formed on said sapphire substrate by using an organometallic compound vapor phase epitaxy at a growth temperature lower than that of said gallium nitride group compound semiconductor.

46. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 38, wherein said buffer layer is formed on said sapphire substrate by using an organometallic compound vapor phase epitaxy at a growth temperature lower than that of said gallium nitride group compound semiconductor.

47. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 39, wherein said buffer layer is formed on said sapphire substrate by using an organometallic compound vapor phase epitaxy at a growth temperature lower than that of said gallium nitride group compound semiconductor.

48. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 40, wherein said buffer layer is formed on said sapphire substrate by using an organometallic compound vapor phase epitaxy at a growth temperature lower than that of said gallium nitride group compound semiconductor.

49. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 41, wherein said buffer layer is formed on said sapphire substrate by using an organometallic compound vapor phase epitaxy at a growth temperature lower than that of said gallium nitride group compound semiconductor.

22/ 50. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 42, wherein said buffer layer is formed on said sapphire substrate by using an organometallic compound vapor phase epitaxy at a growth temperature lower than that of said gallium nitride group compound semiconductor.

22/ 51. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 43, wherein said buffer layer is formed on said sapphire substrate by using an organometallic compound vapor phase epitaxy at a growth temperature lower than that of said gallium nitride group compound semiconductor.

22/ 52. (Original) A method for producing a gallium nitride group compound semiconductor according to claim 44, wherein said buffer layer is formed on said sapphire substrate by using an organometallic compound vapor phase epitaxy at a growth temperature lower than that of said gallium nitride group compound semiconductor.

~~53-118 (Canceled)~~

35 119. (Previously presented) A method for producing a gallium nitride group compound semiconductor according to claim 20, wherein said carrier concentration ranges from  $1 \times 10^{17}/\text{cm}^3$  to  $1 \times 10^{19}/\text{cm}^3$ .

36 120. (Previously presented) A method for producing a gallium nitride group compound semiconductor according to claim 22, wherein said carrier concentration ranges from  $1 \times 10^{17}/\text{cm}^3$  to  $1 \times 10^{19}/\text{cm}^3$ .

27 121. (Previously presented) A method for producing a gallium nitride group compound semiconductor according to claim 24, wherein said carrier concentration ranges from  $1 \times 10^{17}/\text{cm}^3$  to  $1 \times 10^{19}/\text{cm}^3$ .

28/ 122. (Previously presented) A method for producing a gallium nitride group compound semiconductor according to claim 119, wherein said gallium nitride group compound semiconductor is formed on or above a buffer layer which is formed on a sapphire substrate.

29/ 123. (Previously presented) A method for producing a gallium nitride group compound semiconductor according to claim 120, wherein said gallium nitride group compound semiconductor is formed on or above a buffer layer which is formed on a sapphire substrate.

40/ 124. (Previously presented) A method for producing a gallium nitride group compound semiconductor according to claim 121, wherein said gallium nitride group compound semiconductor is formed on or above a buffer layer which is formed on a sapphire substrate.

41/ 125. (Previously presented) A method for producing a gallium nitride group compound semiconductor according to claim 122, wherein said buffer layer is formed on said sapphire substrate by using an organometallic compound vapor phase epitaxy at a growth temperature lower than that of said gallium nitride group compound semiconductor.

42/ 126. (Previously presented) A method for producing a gallium nitride group compound semiconductor according to claim 123, wherein said buffer layer is formed on said sapphire substrate by using an organometallic compound vapor phase epitaxy at a growth temperature lower than that of said gallium nitride group compound semiconductor.

43/ 127. (Previously presented) A method for producing a gallium nitride group compound semiconductor according to claim 124, wherein said buffer layer is formed on said sapphire substrate by using an organometallic compound vapor phase epitaxy at a growth temperature lower than that of said gallium nitride group compound semiconductor.

44/ 128. (Currently amended) A method for producing a gallium nitride group compound semiconductor according to claim 19, wherein said second n-conduction type of gallium nitride group compound semiconductor layer is formed on said first n-conduction type of gallium nitride group compound semiconductor layer.

129. (Currently amended) A method for producing a gallium nitride group compound semiconductor according to claim 19, further comprising:

after said forming said first n-conduction type of gallium nitride group compound semiconductor layer and before said forming said second n-conduction type of gallium nitride group compound semiconductor layer, stopping a flow of said silicon-containing gas.

130. (Currently amended) A method for producing a gallium nitride group compound semiconductor according to claim 19, wherein said forming said first n-conduction type of gallium nitride group compound semiconductor layer comprises controlling said resistivity of said first n-conduction type of gallium nitride group compound semiconductor layer to be within a range from  $3 \times 10^{-1} \Omega\text{cm}$  to  $8 \times 10^{-3} \Omega\text{cm}$ .

131. (Currently amended) A method for producing a gallium nitride group compound semiconductor according to claim 130, wherein said resistivity of said first n-conduction type of gallium nitride group compound semiconductor layer is controlled by varying a flow rate of said silicon-containing gas.

132. (New) A method of fabricating a light-emitting element, comprising:  
forming a gallium nitride group compound semiconductor that is produced by using an organometallic compound vapor phase epitaxy, comprising:  
setting a mixing ratio of a silicon-containing gas to at least one other raw material gas during said vapor phase epitaxy at a desired value in a range over which a conductivity of the gallium nitride group compound semiconductor increases substantially proportionally with said mixing ratio so as to obtain a desired conductivity (1/resistivity) of said gallium nitride group compound semiconductor;  
forming a first n-conduction type of gallium nitride group compound semiconductor layer with a high electron concentration by feeding said silicon-containing gas and said at least one other raw material gas at said mixing ratio;  
forming a second n-conduction type of gallium nitride group compound semiconductor layer with a low electron concentration and having a resistivity which is

greater than a resistivity of said first n-conduction type of gallium nitride group compound semiconductor layer, without feeding said silicon-containing gas; and

etching said second n-conduction type of gallium nitride group compound semiconductor layer to expose a surface of said first n-conduction type of gallium nitride group compound semiconductor layer; and

forming an n-electrode on said exposed surface of said first n-conduction type of gallium nitride group compound semiconductor layer.

48/ 133. (New) The method of fabricating a light-emitting element according to claim 132, 48 further comprising:

forming an insulating gallium nitride group compound semiconductor layer on said second n-conduction type of gallium nitride group compound semiconductor layer, said n-electrode being formed on an upper surface of said insulating gallium nitride group compound semiconductor layer.

49/ 134. (New) The method of fabricating a light-emitting element according to claim 133, 49 further comprising:

etching said insulating gallium nitride group compound semiconductor layer to expose a surface of said second n-conduction type of gallium nitride group compound semiconductor layer, said etching said second n-conduction type of gallium nitride group compound semiconductor layer comprising etching said exposed surface of said second n-conduction type of gallium nitride group compound semiconductor layer.

51/ 135. (New) The method of fabricating a light-emitting element according to claim 133, 49 further comprising:

forming an electrode adjacent to said n-electrode on said upper surface of said insulating gallium nitride group compound semiconductor layer.

09/02/02